



MIXING DIRECTIONS:

Flatwork and Patching projects:

- For flatwork use proper forms. For patching projects, clean surfaces thoroughly. When capping old cements surfaces use **Ash Grove** Concrete Adhesive before applying Concrete Mix.
- ➤ Empty contents into a wheelbarrow or applicable container. Add 3¾ quarts of water per bag, stir or mix thoroughly 3 to 5 minutes.
- Use cement trowel to smooth products to a plastic like consistency.
- Use concrete reinforcements when possible.
- Remember! the drier the mix the stronger the concrete

Setting fence posts:

Wet Process - The wet process stabilizes much faster.

- Dig hole to proper size. Place post in hole
- Pour contents directly around post, six inches from surface.
- Mix **Ash Grove** with 3 3/4 quarts of water per bag
- > Tamp six inches of soil around base of post

<u>PSI TEST RESULTS:</u> **Ash Grove** Concrete Mix is independently tested by Kansas City Testing Laboratories. Results of these regularly scheduled tests have determined a rating of 4350 PSI.

Ash Grove CONCRETE MIX

A commercial blend of portland, concrete sand, and limestone gravel designed to meet or exceed ASTM C-287. Excellent for building sidewalks, steps, footers, floors, etc. For any concrete work requiring a thickness of 2" or more.

Easy to follow mixing directions answer the questions most often asked by the consumer. Your concrete projects will be completed with professional results.

| CONCRETE MIX CALCULATING CHART: for concrete slabs 4" thick | | | | | | | | | | | | |
|---|---|---|---|-----|----|----|----|----|----|----|----|-----|
| SQ.FT. | 2 | 4 | 6 | 8 - | 10 | 14 | 18 | 20 | 40 | 60 | 80 | 100 |
| 80# BAGS | 1 | 2 | 3 | 4, | 5 | 7 | 9 | 10 | 20 | 30 | 40 | 50 |
| SQ. FT. | 2 | 4 | 6 | 8 | 10 | 14 | 18 | 20 | 40 | 60 | 80 | 100 |
| 60#BAGS | 2 | 4 | 5 | 6 | 7 | 10 | 14 | 15 | 30 | 45 | 60 | 72 |

YIELD: 80 LB approx. 2/3 cu.ft. 60 LB approx. 1/2 cu.ft.

HOW TO CALCULATE CONCRETE VOLUME:

Width (ft) X Length (ft) X Thickness (in)

12 = CUBIC FEET

NOTE: One cubic yard equals 27 cubic feet

MATERIALS PACKAGING CORPORATION

23018 S. 291 Hwy * Harrisonville, MO 64701

Ph: 816-380-4473 * Toll Free: 800-597-9061 * Fax: 816-380-6771

You can count on one source for all of your cement, concrete repair, and cement mix